

Specifications

These block magnets are 0.25 inch (6.4mm) long, 0.25 inch (6.4mm) wide, and 0.1 inch (2.5mm) thick. They are composed of grade 40 neodymium iron boron magnetic material and are plated in nickel-copper-nickel for a shiny corrosion resistant finish. Their individual pull force is approximately 2.4 lbs. Max Working Temperature - 176 F (80 C).



Part Number	NSN0610
Imperial Dimensions	0.25 inch long x 0.25 inch wide x 0.1 inch thick
Metric Dimensions	6.35mm long x 6.35mm wide x 2.54mm thick
Material	Sintered Neodymium-Iron-Boron (NdFeB)
Shape	Block
Plating	Ni-Cu-Ni (Nickel)
Magnetization Direction	Thickness
Grade	N40
Pull Force	2.41[1093]
Surface Field	3304
Packaging	Magpak Tube
UPC	897970000105
Magnet Quantity	50
Brand	Magcraft
Maximum Operating Temperature	80 Deg C (176 Deg F)
Maximum Energy Product Bhmax (MGOe (kJ/m ³))	38-41 [302-326]
Remanent Flux Density Br (kG (T))	12.5-12.8 [1.25-1.28]
Coercivity HcB (kOe (kA/m))	≥11.3 [≥923]
Intrinsic Coercivity Hcj (kOe (kA/m))	≥12.0 [≥995]
Dimensional Tolerance	+/-0.005"
Density ρ (g/cm ³)	≥7.45
Compression Strength (Mpa)	600-1200
Bending Strength (Mpa)	150-380
Vickers Hardness (HV)	460-660
Recoil Permeability (μrec)	1.05
Electrical Resistance (Ω·mm ² /m)	1.25-1.55
Curie Temperature Tc (°C)	310
Thermal Expansion Coefficient 100°C // (x10 ⁻⁶ /K)	6
Thermal Expansion Coefficient 100°C ⊥ (x10 ⁻⁶ /K)	-1

