

Specifications

These ring magnets are 1.000 inch (25.4mm) diameter, 0.500 inch (12.7mm) inside diameter and 0.125 inch (3.2mm) thick. They are magnetized through the thickness. They are composed of grade 40 neodymium iron boron magnetic material and are plated in nickel-copper-nickel for a shiny corrosion resistant finish. Their individual pull force is approximately 5.4 lbs. Maximum working temperature is 176 F (80 C).



Part Number	NSN0616
Imperial Dimensions	1 inch outside diameter x 0.5 inch inside diameter x 0.125 inch thick
Metric Dimensions	25.4mm outside diameter x 12.7mm inside diameter x 3.175mm thick
Material	Sintered Neodymium-Iron-Boron (NdFeB)
Shape	Ring
Plating	Ni-Cu-Ni (Nickel)
Magnetization Direction	Thickness
Grade	N40
Pull Force	5.35[2427]
Surface Field	3000
Packaging	Magpak Tube
UPC	875661000160
Magnet Quantity	4
Brand	Magcraft
Maximum Operating Temperature	80 Deg C (176 Deg F)
Maximum Energy Product Bhmax (MGOe (kJ/m3))	38-41 [302-326]
Remanent Flux Density Br (kG (T))	12.5-12.8 [1.25-1.28]
Coercivity HcB (kOe (kA/m))	≥11.3 [≥923]
Intrinsic Coercivity HcJ (kOe (kA/m))	≥12.0 [≥995]
Dimensional Tolerance	+/-0.005"
Density ρ (g/cm3)	≥7.45
Compression Strength (Mpa)	600-1200
Bending Strength (Mpa)	150-380
Vickers Hardness (HV)	460-660
Recoil Permeability (μrec)	1.05
Electrical Resistance (Ω·mm2/m)	1.25-1.55
Curie Temperature Tc (°C)	310
Thermal Expansion Coefficient 100°C // (x10 ⁻⁶ /K)	6
Thermal Expansion Coefficient 100°C ⊥ (x10 ⁻⁶ /K)	-1

